



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey

Dated 16 July 2003

Patents Form 1/77

Patents Act 1977
(Rule 16)The
Patent
Office

THE PATENT OFFICE

12 JUL 2002

RECEIVED BY FAX

12JUL02 E732878-1 002942
R01/7700 0.00-0216180.0

1/77

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1.	Your reference	P2639-GB		
2.	Patent application number <i>(The Patent Office will fill in this part)</i>	0216180.0		
3.	Full name, address and postcode of the or of each applicant <i>(underline all surnames)</i>	Nelson Stokes Ltd Highfield Road Camelford Cornwall PL32 9RA UK		
	Patents ADP number <i>(if you know it)</i>	842 35 76 00 1		
	If the applicant is a corporate body, give the country/state of its incorporation	UK		
4.	Title of the invention	Multiple Layer Hose, Method of Producing a Multiple Layer Hose and Apparatus therefor		
5.	Name of your agent <i>(if you have one)</i>	K R Bryer & Co 7 Gay Street Bath BA1 2PH		
	"Address for service" in the United Kingdom to which all correspondence should be sent <i>(including the postcode)</i>	10 777 002		
	Patents ADP number <i>(if you know it)</i>			
6.	If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and <i>(if you know it)</i> the or each application number	Country	Priority application number <i>(if you know it)</i>	Date of filing <i>(day / month / year)</i>
7.	If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing <i>(day / month / year)</i>	
8.	Is a statement of inventorship and of right to grant of a patent required in support of this request? <i>(Answer 'Yes' if:</i> a) <i>any applicant named in part 3 is not an inventor, or</i> b) <i>there is an inventor who is not named as an applicant, or</i> c) <i>any named applicant is a corporate body.</i> <i>See note (d))</i>	Yes		

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description	9
Claim(s)	4
Abstract	1
Drawing(s)	2

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translation of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77) One

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11. I/We request the grant of a patent on the basis of this application

Signature

Date

12 July 2002

12. Name and daytime telephone number of person to contact in the United Kingdom Mark R Shelley
01225 428877

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

DUPLICATE

1

**MULTIPLE LAYER HOSE,
METHOD OF PRODUCING A MULTIPLE LAYER HOSE AND
APPARATUS THEREFOR**

5 This invention relates to a multilayer hose, method of producing such a hose and an apparatus therefor, and in particular concerns a flexible hose suitable for use in high pressure hydraulic systems such as vehicle braking systems and the like.

10 Multilayer hydraulic hoses usually comprise an inner layer of elastomeric material surrounded by a first braided layer of filamentary material around which is formed a second braided layer of filamentary material over which is placed an elastomeric outer layer. In many embodiments the elastomeric material of the inner and outer layers is rubber and the braided filamentary material is rayon. The first and second rayon layers act as a reinforcement for high-pressure fluid application.

15 A problem associated with hoses of the above mentioned type is that relative movement between the first and second layers of the braided material can cause degradation of the braided layers over time. Degradation of the layers is particularly significant in applications where high pressure hydraulic hoses are subject to
20 movement, flexure and/or vibrations, for example in motor vehicles where reinforced elastomeric hoses are used to connect wheel brake callipers to the ends of metal brake pipes fixed to the vehicle body.

According to an aspect of the invention a multilayer hose comprises an inner layer

surrounded by a first layer of reinforcement material around which is formed a second layer of reinforced material and over which is placed an outer cover, in which the two reinforcement layers have an intermediate layer of elastomeric material applied as a water-based emulsion.

5

The intermediate layer between the layers of reinforced material provides a tougher and longer life hose since the intermediate layer reduces movement between the layers of reinforcement material. The hose of the above aspect of the invention can be produced in a cost effective manner and environmentally conscious way compared
10 with more traditional methods using solvent based rubber.

Preferably, the intermediate layer has a moisture content substantially in the range 0.5 to 1.5%. It is necessary to reduce the moisture content of the intermediate layer to prevent blistering of the outer layer when heat is applied during the vulcanisation
15 process. It is preferred that the moisture content is 1% or less by weight since blistering can occur in the outer layer during vulcanisation if the moisture content is greater than 1%.

Preferably, the intermediate layer comprises a water-based rubber. It is preferred that
20 the reinforcement layers are bonded together using a water based rubber which readily bonds the reinforcement layers together.

In preferred embodiments, the intermediate layer comprises a water based neoprene rubber.

Preferably, at least one of the said first and second reinforcement layers comprises a layer of braided filamentary material. This readily enables the hose to contain high-pressure fluid without distortion or rupture of the hose in use.

5

The said first and second reinforcement layers may comprise the same or similar material. It is preferred that both the first and second reinforcement layers comprise braided rayon filaments treated with resorcinol formaldehyde solution. Alternatively Kevlar (rtm) or PVA may be used in place of rayon – the first is most suitable for the first braid and the second for the second braid.

10

Preferably, the said inner layer and outer cover comprise internal and external flexible resilient layers. In preferred embodiments, the internal and external flexible resilient layers comprise an elastomeric material. This readily enables the hose to be used in applications where pressure and movement of the hose is required, for example in vehicle braking systems.

15

According to another aspect of the invention there is a method of producing a multilayer hose of the type comprising internal and external flexible resilient layers between which is located a reinforcement layer, in which inner and outer reinforcement layers have an intermediate bonding layer; the said method comprising the steps of: providing a first reinforcement layer over the said internal flexible resilient layer; applying a water-based elastomeric emulsion over the said first reinforcement layer to form an intermediate layer; drying the said water-based

20

emulsion to reduce the moisture content thereof; providing a second reinforcement layer over the said elastomeric layer and, before or after the outer layer is applied, curing the said elastomeric layer to bond the two reinforcement layers together preferably the drying step comprises the step of passing air over the said emulsion.

- 5 In the above mentioned method conventional drying methods may be employed in the production process to reduce the moisture content of the water based emulsion when forming the intermediate layer. By applying the intermediate layer as a water based emulsion the use of solvent based rubbers can be avoided. This is particularly advantageous since the drying air can be vented directly to the atmosphere when a
- 10 water-based emulsion is used. Environmental regulations do not allow solvents to be dried in the same way and significant costs are therefore usually associated with treating and/or recovering waste solvent products during drying.

- In preferred method, the step of applying the said water based emulsion comprises the
- 15 step of feeding the said internal resilient layer and said first reinforcement layer into a reservoir of the said emulsion. In this way it is possible to readily achieve an even coating of the water based emulsion over the surface of the reinforcement layer to be coated.

- 20 The braided reinforcement layer or layers readily provides a flexible layer or reinforcement within the hose for containing pressurised fluid in the hose.

Preferably, at least one of the said first and second reinforcement layers comprises a layer of filamentary material and the step of applying the said reinforcement layer(s)

5

comprises the step of braiding the said filamentary material over the surface of a respective adjacent inner layer. In this way it is possible to produce a multilayer hose according to the first mentioned aspect of the invention in a continuous production environment. This readily enables the multilayer hose to be produced in a cost
5 effective, economical and timely manner.

According to a further aspect of the invention there is provided an apparatus for producing a multilayer hose having inner and outer flexible resilient layers with two braided filamentary layers between them and an intermediate water-based elastomeric
10 emulsion bonding layer between the said braided layers, the said apparatus comprising: a first braiding station, an application station at which water-based elastomeric emulsion is applied, a drying station at which moisture content of the said elastomeric bonding layer is reduced to a predetermined level, and a second braiding
station at which a further filamentary braided layer is formed over the intermediate
15 layer.

Preferably, the application station comprises a reservoir for the water-based emulsion and means for feeding the inner layers of the hose through the emulsion.

20 In preferred embodiments, the said drying station comprises air drying means for reducing the said moisture content from the said intermediate layer. The air drying means readily enables the moisture content of the intermediate layer to be reduced to less than 15%, preferably in the region 7-10% in a preliminary drying step.

The drying station may further comprise infrared drying means for further reducing the moisture content from the said intermediate layer. This readily enables the moisture content to be reduced to less than 1%. With the moisture content reduced to 1% or less blistering of the outer layer during vulcanisation can be avoided. Curing
5 of the hose is achieved at high temperature by passing it through a liquid salt bath at 195°C (salt melts at 175°C). as an alternative, it is known to use superheated steam in an autoclave.

The combined drying processes, that is during interleaf application, and prior to
10 application of the outer cover and subsequent vulcanisation, reduces the moisture content to a level where it has no affect on the finished product.

Various embodiments of the invention will now be more particularly described, by way of example, with reference to the accompanying drawings image.

15 Figure 1 is a perspective view of a multilayer hose with each layer cut back to show the detail of each layer of the hose; and

Figure 2 is a schematic view of an apparatus suitable for producing the multilayer hose of Figure 1.

20 Referring to Figure 1 a multilayer hose 10 comprises an inner layer 12 of an elastomeric rubber, a first layer of reinforcement material 14 which comprises braided rayon filaments treated with resorcinol formaldehyde solution, an intermediate layer 16 of an elastomeric water based neoprene rubber, a second layer of reinforcement material 18 comprising braided rayon filaments, and an outer elastomeric rubber layer

20. The layers 12 to 20 are arranged concentrically and coaxially with respect to one another in a circular cross section hose, only part of which is shown in the drawing of Figure 1. The layers 12 to 20 constitute a flexible resilient hose suitable for use in a high-pressure applications such as in a hydraulic or pneumatic system, for example
5 in a vehicle hydraulic braking system.

The intermediate layer 16 which is applied as a water based emulsion bonds the inner and outer braided reinforcement layers 14 and 16 together such that only limited relative movement between the reinforcement layers is possible, and give the
10 additional property that it improves (ie lowers) water permeability to allow the hose to resist water penetration better even over long periods of use in automotive environments where spray is present.

The water based neoprene rubber of the intermediate layer 16 comprises less than 1%
15 moisture to prevent or at least reduce the likelihood of blistering of the outer layer 20 due to gaseous expansion of the moisture during vulcanisation.

Referring now to Figure 2 which schematically illustrates a production apparatus for producing the hose of Figure 1 according to a method of one aspect of the present
20 invention. As shown in the drawing the apparatus comprises a first braiding station 22 for braiding a first filamentary layer of rayon filaments over the external surface of the inner layer 12. The two layer hose is fed continuously from the braiding station 22 over rollers 24, 26 and is immersed in a reservoir 28 comprising a water based emulsion of neoprene rubber which coats the reinforced layer 14 as it is fed through

8

the reservoir 28. The coated hose exits the reservoir 28 by means of a further roller 30 and passes through a wiper station 32 which removes excess emulsion from the hose, before passing into an air drying station 36. In the air drying station air is passed over the coated hose until the moisture content is reduced to between 7 and 10% of the emulsion material forming the intermediate layer 16. On leaving the drying station 36 the coated hose is fed to a second braiding station 38 where the second and radially outermost reinforcement layer 18 is braided onto the outer surface of the intermediate layer 16 with the intermediate layer bonding the first and second braided layers 14 and 18 together. After this and immediately prior to application of the outer coating the hose is passed through an infrared drier and into a cross head extruder where the outer cover is applied.

The outer layer 20 which comprises a flexible resilient material such as rubber is then extruded over the outer surface of the layer at an extrusion station 40 downstream of the second braiding station 38.

Although aspects of the invention have been described with reference to the embodiments shown in the accompanying drawings it is to be understood that the invention is not limited to those precise embodiments and that there is changes and modification maybe effected without exercise of further inventive skill. For example in the method described with reference to Figure 2 the water based neoprene rubber emulsion can be applied by spraying or wiping it onto the outer surface of the braided layer 14. In addition other water-based emulsions other than neoprene rubber may be used in other embodiments of the invention.

It will be appreciated that although there is no absolute required thickness for the intermediate layer 16 a minimum thickness can be determined in accordance with the adhesion that is achieved between the braided layers 14 and 18 by the intermediate
5 layer 16. In addition it is to be understood that the moisture content of the emulsion and the particle size thereof is not critical to the various aspects of the present invention disclosed herein.

10

CLAIMS

1. A multilayer hose comprising an inner layer surrounded by a first layer of reinforcement material around which is formed a second layer of reinforced material
5 and over which is placed an outer cover, in which the two reinforcement layers have an intermediate layer of elastomeric material applied as a water-based emulsion.
2. A hose as claimed in Claim 1 wherein the intermediate layer has a moisture content substantially in the range 0.5 to 1.5%.
- 10 3. A hose as claimed in Claim 2 wherein the moisture content is substantially 1%.
4. A hose as claimed in any one of Claims 1 to 3 wherein the intermediate layer
15 comprises a water based rubber.
5. A hose as claimed in Claims 4 wherein the intermediate layer comprises a water based neoprene rubber.
- 20 6. A hose as claimed in any preceding claim wherein at least one of the said first and second reinforcement layers comprises a layer of braided filamentary material.
7. A hose as claimed in any preceding claim wherein the said first and second reinforcement layers comprise the same or similar material.

11

8. A hose as claimed in any preceding claim wherein the said inner layer and outer cover comprise internal and external flexible resilient layers.

9. A hose as claimed in Claim 8 wherein the internal and external flexible
5 resilient layers comprise an elastomeric material.

9. A method of producing a multilayer hose of the type comprising internal and external flexible resilient layers between which is located a reinforcement layer, in which inner and outer reinforcement layers have an intermediate bonding layer; the
10 said method comprising the steps of:

providing a first reinforcement layer over the said internal flexible resilient layer;

applying a water-based elastomeric emulsion over the said first reinforcement layer to form an intermediate layer;

15 drying the said water-based emulsion to reduce the moisture content thereof;

providing a second reinforcement layer over the said elastomeric layer and subsequently curing the said elastomeric layer to bond the two reinforcement layers together.

20 10. A method as claimed in Claim 9 wherein the said drying step comprises the step of passing air over the said emulsion.

11. A method as claimed in Claim 9 or Claim 10 wherein the moisture content of the said intermediate layer is reduced to lie substantially in the range of 0.5 to 1.5%

12

by weight in the drying step.

12. A method as claimed in any one of Claims 9 to 12 wherein the said emulsion comprises a water based rubber.

5

13. A method as claimed in Claim 12 the said emulsion comprises a water based neoprene rubber.

14. A method as claimed in any one of Claims 9 to 13 wherein the step of
10 applying the said water based emulsion comprises the step of feeding the said internal resilient layer and said first reinforcement layer into a reservoir of the said emulsion.

15. A method as claimed in any one of Claims 9 to 14 wherein at least one of the said first and second reinforcement layers comprises a layer of filamentary material
15 braided and the step of applying the said reinforcement layer(s) comprises the step of braiding the said filamentary material over the surface of a respective adjacent inner layer.

16. Apparatus for producing a multilayer hose having inner and outer flexible
20 resilient layers with two braided filamentary layers between them and an intermediate water-based elastomeric emulsion bonding layer between the said braided layers, the said apparatus comprising: a first braiding station, an application station at which water-based elastomeric emulsion is applied, a drying station at which moisture content of the said elastomeric bonding layer is reduced to a pre-determined level, and

13

a second braiding station at which a further filamentary braided layer is formed over the intermediate layer.

17. Apparatus as claimed in Claim 16 wherein the said application station
5 comprises a reservoir for the said water based emulsion and means for feeding the inner layers of the hose through the said emulsion.

18. Apparatus as claimed in Claim 16 or Claim 17 wherein the said drying station
comprises air drying means for reducing the said moisture content from the said
10 intermediate layer.

19. Apparatus as claimed in Claim 18 wherein the said drying station further
comprises infrared drying means for further reducing the moisture content from the
said intermediate layer.

15

20. A multilayer hose substantially as hereinbefore described with reference to the accompanying drawings.

21. A method substantially as hereinbefore described with reference to the
20 accompanying drawings.

22. Apparatus for producing a multilayer hose substantially as hereinbefore described with reference to the accompanying drawings.

ABSTRACT
MULTIPLE LAYER HOSE,
METHOD OF PRODUCING A MULTIPLE LAYER HOSE AND
APPARATUS THEREFOR

5

In one aspect the present invention provides a multilayer hose comprising an inner layer surrounded by a first layer of reinforcement material around which is formed a second layer of reinforced material and over which is placed an outer cover, in which
10 the two reinforcement layers have an intermediate layer of elastomeric material applied as a water-based emulsion.

In another aspect of the invention there is a method of producing a multilayer hose of the type comprising internal and external flexible resilient layers between which is
15 located a reinforcement layer, in which inner and outer reinforcement layers have an intermediate bonding layer; the said method comprising the steps of:

providing a first reinforcement layer over the said internal flexible resilient layer;

applying a water-based elastomeric emulsion over the said first reinforcement
20 layer to form an intermediate layer;

drying the said water-based emulsion to reduce the moisture content thereof;

providing a second reinforcement layer over the said elastomeric layer and subsequently curing the said elastomeric layer to bond the two reinforcement layers together.




FIG 1




FIGURE 2